

# DraftWhite (MED837)

The DraftWhite™ is a rigid white material, targeted for single-material medical applications such as orthopedics and craniomaxillofacial. The material can be combined with other transparent and Vivid colors allowing for a wide range of medical applications. DraftWhite's mechanical and thermal properties are summarized in the table below.

Property	Standard / Procedure	Value
Tensile Strength	D-638-03	40 – 55 MPa (5,800 – 8,000 psi)
Elongation at Break	D-638-05	5 – 20%
Modulus of Elasticity	D-638-04	2,200 – 3,000 MPa (320,000 – 435,000 psi)
Flexural Strength	D-790-03	70 – 85 MPa (10,000 – 16,000 psi)
Flexural Modulus	D-790-04	2,000 – 2,500 MPa (290,000 – 365,000 psi)
HDT, °C @ 0.45MPa	D-648-06	45 – 50 °C (113 – 122 °F)
HDT, °C @ 1.82MPa	D-648-07	45 – 50 °C (113 – 122 °F)
Izod Notched Impact	D-256-06	20 – 30 J/m (0.375 – 0.562 ft-lb/inch)
Water Absorption	D-570-98 24hr	1.1 – 1.5%
Tg	DMA E	52 – 54 °C (126 – 129 °F)
Shore Hardness (D)	Scale D	83 – 86 (Scale D)
Polymerized Density	Scale M	1.17 – 1.18 g/cm <sup>3</sup>

  

System Availability	Minimum Layer Thickness Capability	Support Structure	Available Color
J5 MediJet™	18 microns (0.0007 in.)	SUP710™ (Waterjet removable)	□ White



alphacam GmbH  
Erlenwiesen 16  
D-73614 Schorndorf  
Tel.: +49 (0) 71 81 92 22-0  
info@alphacam.de

alphacam austria GmbH  
Handelskai 92, Gate1 / 2. OG / Top A  
A-1200 Wien  
Tel.: +43 (0) 1 36 19 600-0  
info@alphacam.at

alphacam swiss GmbH  
Zürcherstrasse 14  
CH-8400 Winterthur  
Tel.: +41 (0) 52 262 07-50  
info@alphacam.ch



alphacam.de  
.at  
.ch